Updated: 10.12.2018 Printed: 09.01.2020

## **PAROC Marine Navis Mat 60**







**Short Description** 

Stone wool mat. Also possible to use with facing AluCoat and G4. See "Facings".

Application

Fire and thermal insulation on ships.

The notified body Eurofins Expert Services Ltd. (0809) performed and issued the certificates: Type-Examination (Module B) certificate No. VTT-C-12315-15-18

Nominal Density

60 kg/m<sup>3</sup>

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

### **Dimensions**

Dimensions	
Width x Length	Thickness
Width 600 or 1000 mm, length 2000 - 8000 mm, depending on thickness	30-100 mm
In accordance with EN 822	In accordance with EN 823

# **Packaging**

Package Type

Plastic packs on pallet.

#### **Fire Properties**

Other Fire Properties		
Property	Value	According to
Fire Classification (IMO)	Non-Combustible	IMO FTP 2010 Code Part 1

## **Thermal Properties**

Thermal Conductivity (values announced by manufacturer)			
Property	Value	According to	
Thermal Conductivity in 10 °C, λ <sub>10</sub>	0,032 W/mK	EN 12667	
Thermal Conductivity in 50 °C, λ <sub>50</sub>	0,038 W/mK	EN 12667	

Paroc Group © 2020


Updated: 10.12.2018 Printed: 09.01.2020



Thermal Conductivity in 100 °C, λ <sub>100</sub>	0,045 W/mK	EN 12667
Thermal Conductivity in 150 °C, $\lambda_{150}$	0,054 W/mK	EN 12667
Thermal Conductivity in 200 °C, $\lambda_{200}$	0,063 W/mK	EN 12667
Thermal Conductivity in 300 °C, λ <sub>300</sub>	0,086 W/mK	EN 12667
Thermal Conductivity in 400 °C, $\lambda_{400}$	0,116 W/mK	EN 12667
Thermal Conductivity in 500 °C, λ <sub>500</sub>	0,153 W/mK	EN 12667

Values announced by the manufacturer.

# **Facings**







AluCoat