Updated: 12.03.2018 Printed: 09.01.2020

## **PAROC Marine Wired Mat 80**







Certification Number VTT-C-11348-15-15 / Eurofins Expert

Services Ltd, Kivimiehentie 4, FI-

02150 Espoo. Finland

Short Description Stone wool wired mat with galvanized

net. Also possible to use with facings AluCoat, G1, G2, G4 and G7. See

"Facings".

Application Fire and thermal insulation on ships.

The notified body Eurofins Expert Services Ltd. (0809) performed and issued the certificates: Type-Examination (Module B) certificate No.VTT-C-11348-15-15

Nominal Density 80 kg/m³

Maximum service temperature for PAROC Marine Wired Mat 80 is 640°C. PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

#### **Dimensions**

Dimensions	
Width x Length	Thickness
Width 500/600/900/1000 mm, length 2000 - 8000 depending on thickness. mm	30 - 120 mm
In accordance with EN 822	In accordance with EN 823

## **Packaging**

Package Type Plastic Packs on Pallet

#### **Fire Properties**

Other Fire Properties		
Property	Value	According to
Fire Classification (IMO)	Non-Combustible	IMO FTP 2010 Code Part 1

## **Thermal Properties**

Paroc Group © 2020

Updated: 12.03.2018 Printed: 09.01.2020



Thermal Conductivity (values announced by manufacturer)			
Property	Value	According to	
Thermal Conductivity in 10 °C, λ <sub>10</sub>	0,036 W/mK	EN 12667	
Thermal Conductivity in 50 °C, $\lambda_{50}$	0,040 W/mK	EN 12667	
Thermal Conductivity in 100 °C, λ <sub>100</sub>	0,046 W/mK	EN 12667	
Thermal Conductivity in 200 °C, λ <sub>200</sub>	0,064 W/mK	EN 12667	
Thermal Conductivity in 300 °C, λ <sub>300</sub>	0,089 W/mK	EN 12667	

## **Moisture Properties**

Water Permeability		
Property	Value	According to
Water Absorption, Short Term WS, W <sub>p</sub>	≤ 1 kg/m²	EN 1609

# **Facings**









